

Description: Thixotropic, heavy duty, corrosion inhibiting compound (CIC). Forms a firm, waxy film.

Range of Use: **AV 100D** is applied as a coating to protect metals commonly used in airframe structures and in aerospace components from corrosion. **AV 100D** is applied over **AV 8** penetrating, water displacing CIC.

AV 100D is used in areas of the airframe subject to severe corrosive environments. It can be applied to painted and unpainted surfaces.

Application: **AV 100D** should be applied by spraying.

AV 100D can be sprayed preferably using the specifically designed **AAS -System** (airless application equipment). It is also possible to use the **ACS -System** (airmix application equipment).

Operating instructions and recommendations for using spray equipment are given in the Technical Manual "**Aircraft Corrosion Protection and Control**" available from the local Chemetall Sales Office.

Safety Information: For safety precautions and information on the safe use of this product please see: **Material Safety Data Sheet for AV 100D**.

Relevant Specifications and Approvals: Detailed information is available on the Chemetall website at:

www.aerospace.chemetall.com

PHYSICAL PROPERTIES

Property	Test Method	Value		
Flash Point:	ASTMD 93 EN ISO 2719	38 °C	(100 °F)	minimum
Non-volatile Content:	ASTMD 1644 EN ISO 3251	71,5	% by weight	minimum
Density at 23°C (73 °F):	EN ISO 12185	990 ± 20	kg/m ³	
Coverage:	Calculated	7	m ² /litre	at 100 µm
Application Temperature:		15 to 30 °C	(60 to 85 °F)	
Storage Temperature:		5 to 30 °C	(40 to 85 °F)	
Shelf Life:		36	months	

FILM PROPERTIES

Property	Test Method	Value		
Colour:	Visual	Transparent, beige		
Specific Film Weight:	Weighing	120	g/m ²	
Approximate Film Thickness:		100 - 200	µm	
Drying Time at Ambient Temperature:		6	hour	approx.
Removable with solvent:	AV 980	Yes		
Salt Spray Test:	ASTMB 117	On steel:	> 1000 h (at R _i 1)*	
		On 2024-T3	> 2000 h (at R _i 1)*	
Humidity:	DIN 50017	On steel	> 1000 h (at R _i 1)*	

* Interpretation according to EN ISO 4628-3

Issue: 2005-03-17
Supersedes issue of: 2002-09-13

[®] registered trademark

The above details have been compiled to the best of our knowledge on the basis of thorough tests and with regard to the current state of our long practical experience. No liabilities or guarantees deriving from or in connection with this leaflet can be imputed to us. Reproduction, in whole or in part, only with our express permission.