

JEHIER

Saint Lezin road
P.O. BOX 29
49120 CHEMILLE
France

Tél. : (33) (0)2.41.64.54.00
Fax : (33) (0)2.41.64.54.01

KB 49

DESCRIPTION	:	<i>« KB 49 » is made of 75 microns Mylar foil, coated on one side with a permanent adhesive, protected by a siliconed foil.</i>
WEIGHT PER M2	:	<i>210 g maxi</i>
PEEL STRENGTH	:	<i>> 15 N/25 mm at room temperature. Test rate : 100 mm/minute.</i>
FIRE RESISTANCE :	:	<i>This material meets :</i> <ul style="list-style-type: none">• <i>FAR 25 par. 25.853 if tested according to the 12 s. vertical bunsenburner test, applied on a 0.6 mm aluminium sheet.</i>
REFERENCE	:	<i>KB 49/Width in mm.</i>
CONDITIONING	:	<i>Roll of 50 meters long. Different widths available</i>
APPLICATIONS	:	<i>Moisture barrier foil for floor protection.</i>

page 1/2

Ed. 09/2006

JEHIER

Saint Lezin road
P.O. BOX 29
49120 CHEMILLE
France

Tél. : (33) (0)2.41.64.54.00
Fax : (33) (0)2.41.64.54.01

KB 49

APPLICABLE SPECIFICATION : *ABS5093B
ABS5093B485 for KB49/485 – Width 485 mm
ABS5093B185 for KB49/185 – Width 185 mm*

SHELF LIFE : *Shelf life :
. 24 months from manufacturing date.*

: *Guaranteed rest shelf life :
. Minimum 12 months from delivery date.*

STORAGE CONDITIONS : *Maximum 30 °C at 50 % relative humidity.*

Page 2/2

Ed. 09/2006